

Chemical		5 Minutes	1 Hour	2 Hours	24 Hours
Worksurface Rubber Statfree® Lead-Free T2, Statfree® T2, Statfree® UC, Dissipative Dual Layer Rubber	Acetic Acid	NA	NA	NA	NA
	Ammonia (10%)	NA	NA	NA	NA
	Sulfuric Acid (4%)	NA	NA	NA	NA
	Nitric Acid (10%)	NA	NA	NA	AA
	Hydrochloric Acid (10%)	NA	NA	NA	AA
	Sodium Hydrate (10%)	NA	NA	NA	AA
	Sodium Hypochlorite	NA	NA	NA	NA
	Sodium Carbonate	NA	NA	NA	NA
	Hydrogen Peroxide	NA	NA	NA	NA
	Ethyl Alcohol (50%)	NA	NA	NA	NA
Floor Mat Rubber Statfree® G2, Statfree® i, Statfree® EB, Statfree® Statfree AFR™ Conductive Rubber	Carbonated Drinks	NA	NA	NA	AA
	Coffee	NA	NA	NA	AA
	Citrate Acid	NA	NA	NA	AA
	Petroleum	NA	NA	NA	AA
	Oil ASTM 1	NA	NA	NA	AA
	Oil ASTM 2	NA	NA	NA	AA
	Perchloroethylen	NA	NA	NA	AA & HA
	Mesitylene	NA	NA	NA	NA

Key
NA: No Alteration
AA: Appearance Alteration
HA: Hardness Alteration
SA: Softness - Alteration
CA: Color Alteration
EA: Electrical Alteration

“Chemical transfer from the worksurface may cause contamination that could lead to corrosion of sensitive metallic parts. Solvents and other chemicals handled at the workstation may have damaging effects on the worksurface. The worksurface material should be evaluated for required compatibility during the qualification process..” [ESD Handbook TR20.20 section 10.2.4 Chemical Considerations]

Copyright Desco Industries 2024

